

## 75 Duro Commercial Grade Fluoroelastomer

Product Code: TD-70C

Description: 66% Fluorine commercial grade fluoroelastomer

Specifications: TD-70C Commercial grade Viton™ fluoroelastomer  
Temperature range -20°F - 400°F continuous

<u>Typical Rubber Properties</u>	<u>Test Method</u>	<u>Typical Value</u>
Hardness (Shore A)	ASTM D2240	75±5
Tensile Strength	ASTM D412	1200 psi min
Elongation	ASTM D412	250% min
Compression Set	ASTM D395B	47% max
Fluid resistance	ASTM D471	30% max
Specific Gravity	ASTM D792	1.94 nominal
Color	Visual	Black

- Thickness & Width as specified.
- This is a commercial grade of Viton™ fluoroelastomer based gasket sheet, recommended for use in fuel, hydrocarbon based fluids, and aggressive media.
- This material is based upon 100% fluoroelastomer with a 66% minimum fluorine. No substitutions will be accepted.
- Compression Set, Plied, Method B 25% compression (168 hr @ 175°C)

Viton™ is a registered trade name of The Chemours Company



[www.masstank.com](http://www.masstank.com)  
508-947-8826



**THERMODYN CORPORATION**  
3550 Silica Road, Sylvania Ohio 43560 U.S.A.  
Phone: 419-841-7782 Toll-Free: 1-800-654-6518 (North America only)  
Fax: 419-841-3139 [www.Thermodyn.com](http://www.Thermodyn.com)